

ARMORFLO 2000

Epoxy Self Leveling

ARMORFLO-2000 (Finish) ARMORFLO100 (Primer) Epoxy Self-leveling Floor Coating

Product Description:

ARMORFLO-2000 Epoxy Self-leveling Flooring System is two-component solvent-free epoxy coat. It has a nice appearance, dust-resistant, corrosion-resistant and easy to clean. The flooring system has good bonding with the solid base, good abrasion resistance and durability. Meanwhile, it has certain toughness, brittle-resistance and capacity to withstand significant weight. The compressive strength and impact resistance ability is also excellent.

Advantage of the Finish (Topcoat):

- 1. The surface of the Self-leveling coat is as smooth as the mirror.
- 2. Seamless, non-dusty and easy to clean.
- 3. Solvent-free and environmental.
- 4. Close-grained surface has good corrosion-resistance to various chemicals.
- 5. Have a large range of colors for the customer's reference.

Where to use:

It can be applied in the non-dusty and non-bacteria areas like pharmacy factory, hospital, Precision Machinery, electronic factory, etc.

Configuration of the Flooring System and Requirements for the Base:

- Concrete strength≥C25;
- Flatness: the maximum fall head in 2M distance < 3mm.
- The first layer must have waterproof treatment.

Technical Data:

- Drying Time: Touch dry: 2 hours, Recoat time: 12 hours, Hard dry: 7 days
- Compressive Strength (Mpa): 68
- Impact resistance strength (Kg €m): 65
- Adhesive force grade: 1
- Pencil Hardness (H): 3
- Special gravity 0.95±0.02 1.55±0.05
- Mixing ratio Armorflo 2000A: Armorflo 2000B = 5:1
- Using time 60 min. (15°C) 30 min. (25°C) 15 min.
- (35°C) VOC content ≤2% (after mixing)
- Abrasion resistance(750g/1000r, g): ≤0.03
- Resistance to engine oil, diesel oil for 60 days: no change. Resistance to 20% sulfuric acid for 20 days: no change Resistance to 20% Sodium hydroxide for 30 days: no change Resistance to toluene,

ethanol for 60 days: no change

Service Life: 8 years Shelf Life: 6 months

Application Procedure:

- 1. Substrate preparation: Cleaning up and polishing the surface to remove floating pulp. The surface must be clean, dry and leveled up.
- 2. Primer: Apply Armorflo 100 epoxy high-solid primer by roller. The primer must be even and exhaustive. The primer should be stirred evenly according to the mixing ratio, then applied directly. The quantity of the builders can be decided as per the square meters of the area. Using roller and waiting for 8 hours to construct the next process.

Inspection standards for the primer: even film with certain brightness.

3. Middle Coat: Mix Armorflo 200 A and B with quartz powder. Then using the scraper to apply it on the floor. Please wait for 12 hours to commence the next process.

Inspection standards for the putty: Non-sticky to hand, no softening, no nail print if scratching on the surface. And sanding the middle coat before you start the topcoat application.

Finish: Apply ARMORFLO-2000 epoxy self-leveling finish, using the gear roller during application.

Inspection standards for the putty: The film should be even, no bubbling, uniform color and good scratch resistance.

Maintenance: 5-7 days. Don't use or wash by water and other chemicals.



ARMORSIL MANUFACTURING INCORPORATION

Sede legale: VIA Montello 48,INT #3 Pordenone, Italy. 33170. Tel: + 30256365-16 www.armorsil.com, info@armorsil.com, sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice