

ARMORFLO 100

FIBER REINFORCED CONCRETE RESURFACER

Product Description:

ARMORFLO 100 is a fiber reinforced polymer modified concrete resurfacer, which is trowellable and sprayable. **ARMORFLO 100** is prepared by adding water and provides an aesthetically fresh appearance to old concrete surface, spalled concrete, salt damaged concrete and new concrete marred by rains

Typical Applications:

- **ARMORFLO 100** can be used for restoration of the following areas:
- Industrial floor resurfacing
- Car parks resurfacing
- Petroleum and Gas Station resurfacing
- Elevated slabs and every other concrete requiring resurfacing

Advantages/Benefits:

- Polymer modified and Enhanced Bond
- Micro Silica Enhanced/ Low permeability/
- Shrinkage Compensated/Low Rebound
- Highly Engineered/ Protect Embedded reinforcing Steel

Surface Preparation:

Prepare concrete substrate in accordance with International Concrete Repair Institute (ICRI) Technical Guideline. Remove all unsound concrete and provide a profiled, porous surface. Substrate must be structurally sound, dust-free, and free of grease, oil, dirt, curing compounds, release agents, or any other surface or penetrated contaminants that will adversely affect bond. Pressure wash the surface with a commercial pressure washer (3000 psi, 4 GPM) (21MPa, 0.25 L/s) and allow to fully dry before application.

PRIMING: Apply one coat of **ARMORPRIME 400** acrylic primer to allow for good bonding and adhesive purpose, for a very porous concrete surface ensure that two coat of primer is applied to ensure surface is well saturated with the primer before application.

Application Instruction:

MIXING : Pour 3.3 to 3.8 litres of water into a clean plastic or metal bucket , pour 70% of **ARMORFLO 100** into the clean bucket of water, then mix with a power mixer at 400 RPM, after two minutes of mixing pour the rest of the material and mix until full homogeneity is achieved

Application and Installation:

Pour the material on the area to be resurfaced using a hand trowel or spray gun ,because of the self leveling property of **ARMORFLO 100** the material can easily be finished as desired, using either a trowel or a broom. The level of thickness will also be determined by the application need, but should

be achieved in one application; the mixed material can be applied at a thickness between 3mm and 20 mm. If the mix hardens, it should be disposed, please do not attempt to remix or add water to hardened mix.

Coverage:

The coverage will depend on the level of thickness so desired, However for a 3mm thickness coverage can be between 4 to 5 square Metre.

Technical Data:

Compressive Strength ASTM C109	
1 day	13.8Mpa
7 days	20.7Mpa
28 days	34.5Mpa

Cleaning and Health:

Remove the excess mortar on tools with copious amount of water; if already dry you can remove through mechanical means. Also prolonged contact with skin may occur as it is the case with all cementitious based material, therefore safety gloves and glasses should be used when working.

Packaging and Shelf Life:

ARMORFLO are packed in 20 kg and 25kg bags .Store in a cold dry place. With proper storage material can be stored and used within 12 months.



ARMORSIL MANUFACTURING INCORPORATION

Sede legale: VIA Montello 48,INT #3 Pordenone, Italy. 33170. Tel: + 30256365-16

www.armorsil.com, info@armorsil.com , sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice