

ARMOR ALLBOND UNIVERSAL

Product Description:

Armor AllBond MS Universal is a high quality universal hybrid sealant & adhesive based on MS polymer.

Features & Benefits:

- High quality durable filling and adhesion, capability,
- Does not contain solvent, silicone or isocyanate,
- Very Low VOC content,
- No bubble formation, even in wet and humid conditions,
- Very good UV resistance
- Over-paintable with water based paints,
- No shrinkage
- Primer less adhesion on many different substrates (preliminary test recommended)

Application Areas:

- Connection joints in sheet metal fabrication, sealing of air conditioning systems.
- Elastic bonding in vibrating constructions
- Sealing of floor joints and low movement wall joints
- Sealing joints in containers, cisterns, silos etc.

Instructions:

- Before the application, the tip of the cartridges is cut and a plastic cap is fixed.
- The tip of the cap is cut according to the width of the surface and fixed to the cartridge gun.
- The sausage package is cut from one edge and fixed to a suitable gun. Then the cap nut is screwed to the cylinder of the gun.
- The joints should be filled at one time and without gaps during the application.
- The surface of Armor MS Universal applied in the joints should be smoothed with a dampened spatula, glazing tool, joint iron or by hand immediately.
- If used, the adhesive tape should be removed afterwards.
- The opened packages should be consumed as quickly as possible.
- The contaminated areas and used tools should be cleaned with white spirit or alcohol. It is cleaned only mechanically after cured.
- Joint width/depth ratio should be 2:1.

Consumption (Approx.):

Joint width	10 mm	15 mm	20 mm	25 mm	30 mm
Joint Depth	5mm	8 mm	10 mm	12 mm	15 mm
Joint length /600 ml	12 meters	5 meters	3 meters	2 meters	1,3 meters

Surface Preparation:

Following cleaning procedure and materials are recommended:

Glass	Degrease with alcohol or MEK
Aluminium, light alloys and stainless steel	Degrease with alcohol or MEK
Other Metals	Lightly abrade then degrease as above
Wood	Lightly abrade surface then remove dust
Plastics	Degrease using an agent recommended by plastics manufacturer
Concrete and other alkaline Surfaces	Brush and remove dust

Standards:

Meets or exceeds the requirements of the following specifications:

- The requirements of VOC content specifications in LEED credit EQc4.1 “Low-emitting products” of SCAQMD rule 1168.
- The French VOC requirements for class A+
- CE marked for EN 15651 for façade applications.

Restrictions:

- It must not be used in totally confined spaces where sealant cannot cure due to lack of atmospheric moisture.

- Armor Allbond Universal can be applied to a variety of substrates directly. If not sure, we recommend a preliminary compatibility test.

Storage and Shelf Life:

- They should be protected from water, frost and adverse air conditions.
- They should be kept dry and cool on wooden pallets at between +10°C and +25°C in moisture free conditions.
- The opened products should be consumed immediately.
- Shelf life is maximum 12 months conditional to complying with the aforementioned storage conditions.

Safety and Disposal:

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Properties:

Chemical Base	MS Polymer
Curing System	Moisture
Density	1.40 ± 0.03 gr/ml
Appearance/Color	Paste, White, Black and Grey
Tack Free	Approx. 50 min (23°C and %50 R.H.)
Curing Rate	Approx. 2,5 mm/ 24 hr (23°C and %50 R.H.)
Sagging (ISO 7390)	0 mm
E100 Modulus (ISO 8339)	< 0,4 N/mm ²
Shore A Hardness (ISO 868)	45 ±5
Elongation at Break % (ISO 37)	≥ % 120
Volume Loss	< -%3 (23°C and %50 R.H.)

Tensile Strength (ISO 37)	1,5 – 2,0 N/mm ²
Heat Resistance	-40°C and +90°C
Application Temperature	+5°C and +40°C

Product:

Product Type	Volume	Package
White/Black/Grey	290 ml	12
White/Black/Grey (Sausage)	600 ml	12



ARMORSIL MANUFACTURING INCORPORATION

Sede legale: VIA Montello 48, INT #3 Pordenone, Italy. 33170. Tel: + 30256365-16

www.armorsil.com, info@armorsil.com, sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or

consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice