

ARMOR SILICONE SEALANT

BUILDING AND CONSTRUCTION

Product Description:

A neutral cure, premium performance silicone sealant designed for gap filling and sealing in a wide range of use in building and construction. It combines the advantages of outstanding adhesion to building materials and non-corrosive and odorless

Features & Benefits:

- 100% solvent less silicone,
- Excellent weatherproof and UV resistant,
- No Cracking or Shrinking,
- Water resistant,
- Very low odor and noncorrosive
- Excellent flexibility and adhesion to numerous porous and non-porous
- substrates for large scale construction and glazing applications.
- Resistant to temperature extremes (-60 °C to +180 °C).
- Fast curing, low modulus, high elasticity.
- High viscosity non-slump formula.

Application Areas:

- Weather sealing and joint sealing for walls, windows and doors.
- Glass to glass and glass to aluminium sealing.
- Sealing applications in kitchens and bathrooms.
- Sealing of connection joints in building industry (brick, wall, concrete, PVC, wood, glass etc.).

Instructions:

- Ensure that surfaces to be sealed are clean, dry and grease free.
- The application temperature must be between +5°C and +40°C.
- In order to reduce the deformations of the joints, their depth must be much less than their width, minimum dimensions are 5x5 mm, for wider
- joints the depth should be preferably half of the width and it is adjusted by the use of a backup material.
- After the application, the sealant must be tooled with light pressure within 5 minutes to spread the material against the joint surfaces and to obtain a professional finish.
- Excess uncured sealant may be cleaned with solvent. Cured sealant can be removed barely mechanically.
- Recommended joint widths are >10 mm and < 35 mm.
- Joint width and depth ratio should be about 2:1.

Consumption (Approx.):

Joint width	10 mm	15 mm	20 mm
Joint Depth	6 mm	8 mm	10 mm
Joint length /310 ml	5 meters	2.5 meters	1.5 meters

Surface Preparation:

Following cleaning procedure and materials are recommended:

Glass	Degrease with alcohol or MEK
Aluminium, light alloys and stainless steel	Degrease with alcohol or MEK
Other Metals	Lightly abrade then degrease as above
Wood	Lightly abrade surface then remove dust
Plastics	Degrease using an agent recommended by plastics manufacturer
Concrete and other alkaline Surfaces	Brush and remove dust

Standards:

Meets or exceeds the requirements of the following specifications:

- The French VOC requirements for class A+
- ISO 11600 F & G 20LM.
- CE marked un 15651 for façade, glazing and sanitary applications.
- The requirements of VOC content specifications in LEED credit EQc4.1 “Low-emitting products” of SCAQMD rule 1168.

Restrictions:

- It must not be used in totally confined spaces where sealant cannot cure due to lack of atmospheric moisture.
- Not over paintable.
- Do not use in conjunction with bitumen asphalt, neoprene and certain organic elastomers.
- It is not suitable for food contact applications.
- Do not use to produce swimming pool joints.
- Can yellow if exposed to bleach or HCL based brick cleaners whilst curing.
- Do not use in conjunction with bitumen asphalt, neoprene and certain organic elastomers.

Storage and Shelf Life:

- The shelf life is 15 months if stored in unopened-original package in a dry place at temperatures between +5°C and +25°C.

Safety and Disposal:

Inhalation of the sealant vapor for a long period must be avoided. The application area must be ventilated properly. The uncured sealant must not be contacted for a long period. Cured silicone rubber bears no risk to health. Temperatures between +5°C and +25°C.

Properties:

Basis	Silicone Polymer(Oxime)
Curing System	Neutral
Density (Transparent and Aluminum)	1.02± 0.03 g/ml (ASTM D 792)
Density (Other Colors)	1.20± 0.03 g/ml (ASTM D 792)
Hardness Shore A (Transparent and Aluminum)	17-25 (after 28 days)
Hardness Shore A (Other Colors)	22-32 (after 28 days)
Tensile Strength	≤ 0,4 N/mm ² (23°C and 50% R.H) (ISO 8339)
Temperature Resistance	-60°C to +180°C
Application Temperature	+5°C to +40°C

Elongation At Break (Transparent and Aluminum)	≥ 400% (ASTM D412)
Elongation At Break (Other Colors)	≥350%
Elastic Recovery	Approx. 100% (ISO 7389)
Sagging	0 mm (ISO 7390)

Product: _____

Product Type	Volume	Package
Transparent, White, Black, Aluminum, Grey, Brown	310 ml	24



ARMORSIL MANUFACTURING INCORPORATION

Office Address: 4636 Chestnut Street, Philadelphia, Pennsylvania 19139. Tel: +1 209 813 2466

www.armorsil.com, info@armorsil.com, sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice

PROVIDING ARMOR FOR BUILDING STRUCTURES