

ARMORPATCH 200

RESURFACE WORN, OLD AND SPALLED CONCRETE

Product Description:

ARMORPATCH 200 is a water repellent, corrosion inhibiting, polymer modified shrinkage compensated, fiber reinforced, rapid setting, high strength mortar specially formulated for structural concrete repairs in vertical and horizontal surfaces. **ARMORPATCH 200** has impressive water repellent and waterproofing properties and therefore suitable for areas requiring waterproofing protection. It can be used in the following areas

-) Interior and exterior
-) Leveling and repair of horizontal concrete surfaces
-) Structural repairs
-) Parking & bridge decks
-) Industrial floors

Typical Applications:

ARMORPATCH 200 can be used for all structural concrete repairs such as:

-) Interior and exterior concrete surfaces
-) Repair of horizontal and vertical surfaces
-) Repair concrete sidewalks, concrete spalling
-) Industrial floors
-) Parking lots and bridge decks

Advantages/Benefits:

-) Water repellent and waterproof
-) Recommended for areas requiring moisture remediation
-) Aesthetically nice self leveling and smooth finish
-) Fiber reinforced to eliminate crack and increase strength
-) Good corrosion Inhibition property, therefore protect reinforcements
-) Minimal shrinkage and outstanding resistance to crack
-) Excellent bond strength
-) High abrasion resistance

Surface Preparation:

Prepare concrete substrate in accordance with International Concrete Repair Institute (ICRI) Technical Guideline. Remove all unsound concrete and provide a profiled, porous surface. Substrate must be structurally sound, dust-free, and free of grease, oil, dirt, curing compounds, release agents, or any other surface or penetrated contaminants that will adversely affect bond. Pressure wash the surface

with a commercial pressure washer (3000 psi, 4 GPM) (21MPa, 0.25 L/s) and allow to fully dry before application

PRIMING: in most instances priming will not be needed but for vertical surfaces and very porous concrete Apply one coat of **ARMORPRIME 400** acrylic primer to allow for good bonding and adhesive purpose.

Application Instruction:

MIXING: Pour 3.3 to 3.8litres of water into a clean plastic or metal bucket, pour 70% of **ARMORPATCH 200** into the clean bucket of water, then mix with a power mixer at 400 RPM, after two minutes of mixing pour the rest of the material and mix until full homogeneity is achieved

Application and Installation:

Pour the material on the area to be resurfaced using a hand trowel or spray gun, because of the self leveling property of **ARMORPATCH 200** the material can easily be finished as desired, using either a trowel or a broom. The level of thickness will also be determined by the application need, but should be achieved in one application; the mixed material can be applied at a thickness between 3mm and 20 mm. If the mix hardens, it should be disposed, please do not attempt to remix or add water to hardened mix.

Specification :

ARMORPATCH 200 should be specified for all concrete surfaces requiring repairs and corrosion inhibition.

It is abrasion resistant and restores concrete surface to an aesthetically fine finish.

Technical Data:

Compressive Strength ASTM C109	
1 day	13.8Mpa
7 days	20.7Mpa
28 days	34.5Mpa

Coverage per 20kg:

Coverage at 1/16" (0.16cm) is approximately 8m²(90ft²)

Cleaning and Health:

Remove the excess mortar on tools with copious amount of water; if already dry you can remove through mechanical means. Also prolonged contact with skin may occur as it is the case with all cementitious based material, therefore safety gloves and glasses should be used when working.

Packaging and Shelf Life:

ARMORPATCH 200 is packed in 20 kg and 25kg bags .Store in a cold dry place. With proper storage material can be stored and used within 12 months.



ARMORSIL MANUFACTURING INCORPORATION

) 4636 Chestnut Street, Philadelphia, Pennsylvania 19139 . Tel : +1 209 813 246 +1 415 670 9521
) www.armorsil.com, info@armorsil.com, sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice