

POLYASPARTIC POLYUREA

PA 1070

Product Description:

ARMOR Polyaspartic Polyurea PA 1070 is a 2 component, UV resistant polyaspartic based polyurea system. This new generation aliphatic polyurea coating system is ideal for applications which require excellent color stability. Polyurea coatings are different in both application and performance from spray applied systems. While this system can be applied as a thin coating, it can also be used as a top layer on top of the existing coating. Additionally, it can be also used to increase the corrosion resistance of the metal substrates. It has very high scratch and impact resistance. After the product is completely cured, it forms a glossy, smooth top layer. It can be applied with roller, brush or an airless system.

Features:

- Excellent color stability and UV resistance
- Suitable for exterior and interior applications
- Long working and gelling time
- Fast service time (open to pedestrian traffic after 2-4 hours)
- VOC and odor free
- High abrasion and impact resistance
- Excellent corrosion resistance
- High hydrolysis resistance
- Perfect thermal stability
- Wide color range

Application Areas:

- UV and color stable top coat on existing base coat
- High color stability and gloss requiring swimming pools
- Terraces and roofs
- Water parks, playgrounds and decorative applications
- Wind turbines

Surface Preparation and Application:

- Polyaspartic coating adheres perfectly to dry and clean surfaces like metal and concrete. Application surface should be clean and smooth, free of any dirt, gap or particles. If there is already a coating on the surface, an appropriate polyurethane or epoxy based primer should be applied. After the primer is cured, product could be applied.
- Amine resin component should be stirred very well to prevent pigment settling to achieve color homogeneity. Be careful about the component mixing ratios and avoid bubbles during the mixing process. Mixing process should be between 1-1.5 minutes until the homogenization is obtained. After the mixing product should be rested for 2-3 minutes before application.
- To achieve appropriate coating thickness, application should be applied to all direction (from south to north, east to west) with a roller or brush. If a second layer is needed, it must be applied within 4 hours after the first layer is applied.
- Alternatively airless gun can be also used for its application.

- Wait 2 hours for light pedestrian traffic and 24 hours for full service time. As curing time is affected by temperature and humidity, check real cure time on the site of application.
- All application equipments must be cleaned with acetone, MEK, MIBK and xylene like solvents after application.

Storage and Shelf Life:

Polyurea components are sensitive to moisture. Keep polyurea components in tightly closed containers. Mix amine resin before application. Store polyurea components between 20 -30 °C. It has 9 months of storage time, if stored according to stated conditions.

Safety and Disposal:

Avoid breathing vapors. Avoid contact with skin and eyes. Take precautions during application. Wear suitable protective clothing, gloves and eye/ face protection. Adequate ventilation of the working area is recommended. Refer to SDS sheet prior to use.

Technical Features:

COMPONENT PROPERTIES

	Unit	Method	HDI Prepolymer (A)	Amine Resin (B)
Density (25°C)	g/cm ³	ASTM D 1217	1.15-1.17	1.07-1.1
Viscosity (25°C)	mPa.s	ASTM D 4878	720-750	1000-1100
Shelf life	-----	-----	9 months	9 months

PHYSICAL PROPERTIES

	Method	Data
Chemical structure		A: HDI Prepolymer
		B: Amine Resin
Mix ratio (by weight)	--	40:60 A:B
Consumption (g/cm²)	--	250-500
Recommended thickness (μm)	--	100-250 (for each layer)
VOC content (%)	ASTM D1259	0
Solid content (%)	ASTM D2697	90
Gel time (sec)	--	30-35
Tack free time (sec)	--	50-65
Pedestrian traffic time (hr)	--	0-12
Full curing time (hr)	--	24
Tensile strength (MPa)	ASTM D638	>30
Elongation at break (%)	ASTM D638	4-6
Hardness (Shore D)	ASTM D2240	55±5
Abrasion resistance (mg)	EN ISO 5470-1	<15 (H22, 1000 cycle)

**ARMORSIL MANUFACTURING INCORPORATION**

- 4636 Chestnut Street, Philadelphia, Pennsylvania 19139 . Tel : +1 209 813 246 +1 415 670 9521
- www.armorsil.com, info@armorsil.com, sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice