

ARMORFIX 109

High Performing Non-Slip Tile adhesive for low porosity tiles

Product Description:

ARMORFIX -109 is a high performing, standard setting, cement based tile adhesive. It is suitable for thin and thick bed applications, internal and external applications. ARMORFIX -109 is polymer modified and has excellent anti slip properties.

It is suitable for the fixing of porcelain and ceramic tiles on floor and wall of concrete, concrete block and cement render. It can also be used for the fixing of glass mosaic, stone marble, Pre-cast concrete facings, terrazzo and brick slips.

Advantages:

- High adhesive tensile strength
- Polymer modified and therefore provides strong bond for tiles with low porosity
- Easy to mix and apply
- Non-sag and anti-slip properties with high initial adhesiveness
- Greater workability due to high port life
- For areas requiring flexibility ARMORFIX 109 can be used with ARMOR Super latex to improve Properties

Uses:

For the installation of floor and wall porcelain, ceramic tiles, glass mosaic, stone marble, terrazzo, and brick slips and for fixing of tiles on plaster boards, gypsum plaster and wood. Note that ARMOR Prime 106 is required when ARMORFIX-109 is used on wood, plasterboard and gypsum plaster

Surface Preparation:

The substrate must be fully cured and well prepared, it must be sound, clean, structurally stable, free from dirt, loose particles, efflorescence, chemicals and other contaminants, in order to ensure proper bonding. Standard practice requires at least seven weeks before tiling on concrete and two weeks before tiling on screed.

Application Instruction:

Pour ARMORFIX-109 into a clean plastic or metal bucket containing clean water, pour adequate quantity of ARMORFIX-109 that can be used within the pot life of 2 hours. 20kg of ARMORFIX -110 requires approximately 4 litres of water. Stir with a mixing device or by hand. Let the mixture rest for 10-15 minutes and restart briefly before application. No further water should be added after mixing.

Application and Installation:

Spread ARMORFIX -109 tile adhesive mortar evenly over 1m² area at a time using a notched trowel. Fix tiles

Immediately within the open time of 20 minutes. Please be sure that all areas are covered with ARMORFIX -109 tile adhesive.

GROUTING

Grouting should be done 24 hours after tiling, for SWIMMING pool leave at least 3 days before grouting and at least one week before filling.

Coverage:

For thin solid bed application (3mm thickness) 4-5kg of ARMORFIX -109 will cover approximately 1m². Large tiles may need to have the adhesive buttered to the back as well. Ensure that tiles are well bedded into the adhesive. See further information in the technical section below

Packaging:

Available in 20kg bags and buckets

Technical Data:

Exceeds the requirements of BS EN 12004 for C2T

Bed thickness	3 – 6 mm (may be exceeded in small areas only) Coverage (approx.)
Coverage (approx)	9 kg/m² (solid bed, 6 mm thick)
	4.5 kg/m² (solid bed, 3 mm thick)
	3.0 kg/m² (using a notched trowel with 6 x 6 mm notches)
3.0 kg/m² (using a notched trowel with 6 x 6 mm notches at 12 mm centres)	
Open time	20 minutes
Working time (pot life)	2 hours
Set time	18 – 24 hours
Temperature resistance	-10 to 100°C and frost resistant when set

Water addition	4 litres per 20 kg
Particle size	Up to approx. 0.5 mm

Note: setting times are quoted at 20°C - 30°C and are temperature and humidity dependent.

Cleaning and Health:

Remove the excess mortar on tools with copious amount of water; if already dry you can remove through mechanical means. Also, prolonged contact with skin may occur as it is the case with all cementitious based material, therefore safety gloves and glasses should be used when working.

Shelf Life:

Store in a cool dry place, with proper storage, material can be stored and used within 12 months.



ARMORSIL MANUFACTURING INCORPORATION

Office Address: 4636 Chestnut Street, Philadelphia, Pennsylvania 19139. Tel: +1 209 813 2466

www.armorsil.com, info@armorsil.com, sales@armorsil.com

Limited Warranty

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Safety Data Sheet prior to product use away.

Armorsil Manufacturing supplies products that comply with the properties shown on the current datasheets. In the unlikely event that products supplied are proved not to comply with these properties, then we will replace the non-compliant product or refund the purchase price. Armorsil Manufacturing does not warrant or guarantee the installation of the products as it does not have control over the installation or end use of the products. Any suspected defects must be reported to Armorsil Manufacturing in writing within seven working days of being detected.

Armorsil Manufacturing. Makes no warranty as to merchantability or fitness for a particular purpose and this warranty is in lieu of all other warranties express or implied. Neither seller nor Armorsil Manufacturing shall be liable to the buyer or any third person for any injury, loss or damages of any sort including remote or consequential damages, down time, or delay directly or indirectly resulting from use of or inability to use the product. . The information contained in the latest data sheet supersedes all previously published editions. Visits to site by Armorsil personnel do not constitute supervisory responsibility. Armorsil reserves the right to alter the information contained in this datasheet without prior notice

PROVIDING ARMOR FOR BUILDING STRUCTURES